



In vitro hazard assessment of nanoparticles developed for biomedical applications

Annette Luce, Y Saibi, Isabelle Séverin, Julien Boudon, Nadine Millot,
Marie-Christine Chagnon

► To cite this version:

Annette Luce, Y Saibi, Isabelle Séverin, Julien Boudon, Nadine Millot, et al.. In vitro hazard assessment of nanoparticles developed for biomedical applications. European Society of Toxicology In Vitro (ESTIV) 2016 meeting, Oct 2016, Juan-les-Pins, France. 2016. hal-01986190

HAL Id: hal-01986190

<https://institut-agro-dijon.hal.science/hal-01986190>

Submitted on 18 Jan 2019

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

In vitro hazard assessment of nanoparticles developed for biomedical applications


A. Luce^{ab}, Y. Saïbi^{ab}, I. Séverin^b, J. Boudon^a, N. Millot^a, M. C. Chagnon^b

(a) Laboratoire Interdisciplinaire Carnot de Bourgogne (ICB), UMR 6303 - CNRS/Université de Bourgogne
(b) INSERM U866, Derttech « Packtox », Agrosupdiijon.


Nanotechnology is a growing sector in industry for twenty years and nanomaterials are currently used in numerous industrial applications. Their interest is based on their dimensions and their shape that give them very particular technological and biological properties. However, the development of these nanoparticles, their industrial preparation and integration into various products already involve an initial increased of human exposure (*via* inhalation, percutaneous and oral route). Another exposure pathway exists and is represented by drug injections. The risks associated with these new technologies and new products are still unclear. After a characterization step (zeta potential, TEM, TGA, DLS, XPS, IR measurements ...), different toxicological endpoints were analyzed *in vitro*. However, bioassay protocols need to be adapted to nanoparticles. Cytotoxicity was assessed with the RNA synthesis inhibition assay, which is an early very sensitive sublethal bioassay. Oxidative stress was detected using DCF-DA assay for a sensitive and rapid quantitation of oxygen-reactive species. For genotoxicity, the comet assay performed in presence of Formamido-Pyrimidine-Glycosylase (FPG) detects low levels of DNA damage relative to DNA oxidative damage. Finally a short-term cell transformation assay (CTA) was performed, using the Bhas 42 cell line to distinguish between tumor initiators and promoters properties. Nanoparticles (SPIONs and titanate nanotubes (TiONts)) didn't induce any cytotoxic, genotoxic and oxidative response after a 24h treatment with concentrations up to 100 µg/mL in the human HepG2 cell line. However, TiONts induced a positive dose dependent response in the CTA assay at the initiation step (1-10 µg/mL).

SPIONs-NH₂ SuperParamagnetic Iron oxide Nanoparticles


➤ Controllable size




➤ Coupling possibilities with many biologicals entities



¹Boudon and al. Chem. Comm. 49 (67), (2013) 7394 -7396



➤ Special magnetical properties allowing their use in various biomedical applications:





²Levy and al. PNAS, published online April 2010


TiONts-NH₂ Titanate Nanotubes

➤ Nanotubes diameter 10 nm

➤ Nanotubes length ~150 nm




➤ Applications area



Biomedical applications

- ◆ TiONts are developed as sensors (dopamine) and bone regeneration.
- ◆ Therapeutic nanovectors (DNA transfection and radiosensitiser).



³Mirjolet and al. Radioth. Oncol. 108, (2013) 136
⁴Papa Nanotoxicology 7 (6), (2013) 1131

Genotoxicity assay

Comet assay- fpg

▪ Very sensitive assay to detect and quantify DNA breaks. The presence of formamidopyrimidine DNA glycosylase (fpg) allows the detection of specific genotoxic damages.

Principle: Detect single and double DNA strand breaks and alkali-labile sites after an electrophoresis in alkaline condition (pH = 13) and DNA staining with a fluorescent intercalating agent (propidium iodide)⁵.

T+ → methyl methanesulfonate C₂H₆O₃S (25 µM)




Figure 1 : Evaluation of genotoxicity in HepG2 cells incubated 24 hours in the presence of different concentrations of SPIONs. 3 independent experiments were performed and the results were averaged and expressed as score⁶.






Figure 2 : Evaluation of genotoxicity in HepG2 cells incubated 24 hours in the presence of different concentrations of TiONts. 3 independent experiments were performed and the results were averaged and expressed as score⁶.

➤ No genotoxic effect on a wide range of non-cytotoxic concentrations using the comet assay on HepG2 cells.

⁵Domijan and al. Toxicology 222, (2006) 53-59

⁶Collins and al. Molec. Biotech. 26, (2004) 249-261




Formula score =
(comets class 0 x 0)
+ (comets class 1 x 1)
+ (comets class 2 x 2)
+ (comets class 3 x 3)
+ (comets class 4 x 4)

Oxidative stress

DCF-DA assay

▪ Simple assay to detect ROS production by HepG2 cell metabolism.

Principle: Fluorometric assay using the cell permeant 1',3'-dichlorodihydrofluorescein diacetate (H₂DCFDA). Fluorescence is proportional to ROS production.



T+ → Tert-butyle hydroperoxide (tBHP)
15 µM

➤ ROS production induced by SPIONs and TiONts at high concentrations.




Figure 4 : Fluorescence induced by ROS production after a 24h exposure to SPIONs - NH₂.




Figure 5 : Fluorescence induced by ROS production after a 24h exposure to TiONts - NH₂.

CTA


Cell Transformation Assay

▪ Short term assay to determine the carcinogenicity of nanoparticles (90% of carcinogenic substances detected⁷).

Principle: Observations of morphological change of Bhas 42 cells in foci. A significant increase in the number of foci shows a potential carcinogenicity (initiator and/or promoter effect)⁸.

Negative foci

Positive foci



⁷EFSA Journal (2011)

⁸Ayako and al. Mutation Research 725, (2011) 57 - 77




Figure 7 : Number of foci / well induced after a 3 day exposure with TiONts in the growth phase in the initiation assay.




Figure 8 : Number of foci / well induced after an 11 day exposure with TiONts during stationary phase in the promotion assay.




Figure 9 : Number of foci / well induced after an 11 day exposure with SPIONs during the stationary phase in the promotion assay.

T+ → 3-Methylcholanthrene (MCA) 1 µg/mL

T+ → 12-O-tetradecanoylphorbol-13-acetate (TPA) 50 ng/mL

➤ TiONts induced a statistically significant initiation with a dose-effect (starting at 1 µg/mL) in the Bhas42 cells, promotion response was equivocal with absence of dose response.
➤ SPIONs induced also an equivocal promotion effect without dose response.

TEM

Transmission Electron Microscopy




Figure 5 : TEM images of HepG2 cells incubated 4 hours in the presence of titanate nanotubes (a-b) and iron oxide nanoparticles (c-d) to a concentration of 100 µg/mL. Figures above show that the TiONts and the SPIONs have a vesicular localization.

➤ A vesicular localization of TiONts and SPIONs was observed, probably due to two pathways: endocytosis and diffusion⁹.

⁹Mirjolet and al. Radiotherapy and Oncology 108, (2013) 136-142

Discussion/conclusions

- ❖ SPIONs or TiONts were not genotoxic for HepG2 cells.
- ❖ TiONts and SPIONs induced ROS production but only at the IC₅₀ (50 µg/mL) determined previously by RNA synthesis inhibition assay. This concentration is however higher than the dose injected by IV to mouse in *in vivo* assay (30 µg/mL) to check the target tissue and the elimination of nanoparticles.
- ❖ TiONts induced initiation and then a potential carcinogenicity, mutagenic assay is running in the laboratory using mammalian cells.
- ❖ Concerning the equivocal promotion data observed with nanoparticles; experiments are currently performed to check this response.