

Controlled diffusion by thin layer coating: The intricate case of the glass-stopper interface

Julie Chanut, Jean-Pierre Bellat, Régis Gougeon, Thomas Karbowiak

► To cite this version:

Julie Chanut, Jean-Pierre Bellat, Régis Gougeon, Thomas Karbowiak. Controlled diffusion by thin layer coating: The intricate case of the glass-stopper interface. Food Control, 2021, 120, pp.107446. 10.1016/j.foodcont.2020.107446 . hal-02989078

HAL Id: hal-02989078 https://institut-agro-dijon.hal.science/hal-02989078

Submitted on 24 Aug2022

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers. L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



Distributed under a Creative Commons Attribution - NonCommercial 4.0 International License

Controlled diffusion by thin layer coating: the 1 intricate case of the glass-stopper interface 2 3 Julie Chanut ^{a,b}, Jean-Pierre Bellat ^b, Régis D. Gougeon ^{a,c}, Thomas Karbowiak ^{a,*} 4 5 6 ^a Univ. Bourgogne Franche-Comté, Agrosup Dijon, PAM UMR 02 102, 1 Esplanade Erasme, 7 21000 Dijon, France 8 ^b Univ. Bourgogne Franche-Comté, Laboratoire Interdisciplinaire Carnot de Bourgogne, UMR 9 6303 CNRS, 9 Avenue Alain Savary, 21000 Dijon, France 10 ^c Univ. Bourgogne Franche-Comté, Institut Universitaire de la Vigne et du Vin, 1 rue Claude Ladrey, 21000 Dijon, France 11 12 13 14 **Corresponding Author:** 15 Prof. Thomas Karbowiak, Univ. Bourgogne Franche-Comté, AgroSup Dijon, PAM UMR 02 102, 16 1 Esplanade Erasme, 21000 Dijon, France, phone number: +33380772388, 17 *E-mail: thomas.karbowiak@agrosupdijon.fr 18 19 20 21

1

22 ABSTRACT

A comprehensive study was carried out to investigate the critical role played by the interface between the stopper and the bottleneck on oxygen penetration into the bottle, as well as the effect of surface treatment of the stopper. First, the compression of micro-agglomerated cork, at close to 40% (similar to that of a cork stopper in a still wine bottleneck), had a very limited effect on the oxygen transfer. Second, once a cork was inserted into a glass bottleneck without any surface treatment, up to 99% of the total oxygen transfer took place at the stopper-bottleneck interface. Third, when the cork surface was coated with a paraffin-silicone mixture, there was almost no oxygen transfer at the interface. Although initially used as a slippery agent for easier uncorking, the surface coating of the stopper, as a thin layer of several hundred nanometers, had a remarkable and unexpected impact on the control of the oxygen transfer. KEYWORDS gas transfer, oxygen, agglomerated cork, interface, surface treatment.

49 1. INTRODUCTION

50

51 During wine conservation in a bottle, the control of oxygen transfer from the outside environment 52 to the wine inside the bottle is a key parameter that determines the wine quality. Many other 53 factors can also influence the evolution of wine during postbottling aging, such as the 54 composition of the wine itself (also related to the wine-making process), the temperature, the 55 relative humidity, the storage position, as well as the amount of oxygen initially present in the 56 bottle (Arapitsas et al., 2014; Lopes, Saucier, Teissedre & Glories, 2006; Lopes et al., 2012; 57 Roullier-Gall et al., 2017; Venturi et al., 2016). However, the oxygen transfer is the most critical 58 factor (Roullier-Gall et al., 2016). For this reason, the choice of the packaging and in particular of 59 the stopper is crucial in providing the best conditions for wine aging (Caloghiris, Waters & 60 Williams, 1997; Crouvisier-Urion, Bellat, Gougeon & Karbowiak, 2018; Karbowiak et al., 2010; 61 Lopes, Saucier, Teissedre & Glories, 2007a; Lopes, Saucier, Teissedre & Glories, 2007b; Waters, 62 Peng, Pocock & Williams, 1996).

63 The transfer of oxygen into the bottle occurs by diffusion through the stopper itself and also at 64 the interface between the glass bottleneck and the cork stopper. The oxygen transfer at the 65 interface between the glass bottleneck and the cork stopper was first investigated experimentally in two studies (Lopes, Saucier, Teissedre & Glories, 2007b; Waters et al., 2001). Lopes et al. and 66 67 Waters et al. measured the oxygen transfer through cork stoppers compressed in a bottleneck 68 with an epoxy glue applied to the stopper-bottleneck interface present on the external surface in 69 contact with the air. Their setup prevented the entry of oxygen through this top part of the cork-70 glass interface but still allowed the transfer that can occur through the lower part of the stopper-71 bottleneck interface once it has passed through the outer surface. A preliminary study by 72 Lagorce-Tachon et al., on natural cork stopper inserted in a bottleneck without surface treatment showed that the global diffusion coefficient through the cork-glass bottleneck system was fifty times higher (5 x 10^{-7} m².s⁻¹) than through the compressed cork stopper alone (8 x 10^{-9} m².s⁻¹) (Lagorce-Tachon et al., 2016).

76 Recently, Karbowiak et al. measured the oxygen transfer through corked bottlenecks and through 77 cork stoppers alone for bottles containing oxidized and nonoxidized white wines(Karbowiak et 78 al., 2019). Their results showed that the effective oxygen diffusion coefficient for the cork 79 compressed in a bottleneck was considerably higher for oxidized wines than for nonoxidized 80 wines, whereas the oxygen diffusion coefficient for the cork stopper alone remained similar in all 81 cases. However, in the studies by Lagorce-Tachon et al. and Karbowiak et al., the diffusion 82 coefficient values were measured on dry cork without taking into account the possible effects of 83 water and ethanol on barrier and mechanical properties of cork. These two studies highlight that 84 the cork stopper-glass bottleneck interface is likely to play an important role in oxygen transfer.

85 With the various types cork stopper currently used (natural or agglomerated), an additional outer 86 layer of a surface treatment product is always applied in the final step of the manufacturing 87 process. The most common coating agents are food-grade paraffin wax, silicone, or emulsions of 88 these two products in a mixture (Lefebvre et al., 2006). They are usually spread in a drum coater 89 to cover the surface of the stoppers, but the method of application and the quantity applied 90 depend on the cork supplier. The primary function of these surface treatments is to facilitate the 91 introduction and especially the extraction of the stopper from the bottleneck at the opening as 92 they reduce the adhesion between the glass and the cork acting as a slippery agent (Chatonnet & 93 Labadie, 2003; Fortes, Rosa & Pereira, 2004; Gonzalez-Adrados et al., 2011). They also improve 94 the tightness to liquids by reducing the risk of leakage and they reduce the kinetics of liquid 95 sorption by the stopper during cork-wine interaction (Gonzalez-Adrados et al., 2008). However,

only a few studies have reported the effect of the coating agents on the transfer of oxygen through
the cork-bottleneck system (Keenan, Gozukara, Christie & Heyes, 1999; Waters, 1997).

98 Keenan et al. determined the oxygen permeability of macrocrystalline paraffin wax coated on 99 natural cork stoppers and calculated the theoretical ingress of oxygen diffusing through a 17 µm 100 layer of macrocrystalline paraffin wax coated on these stoppers. The oxygen transfer through the 101 paraffin layer was not sufficient to cause the wine oxidation. The calculation was made in the 102 case of a continuous coating along the stopper compressed in a cylindrical tube (18.5 mm in 103 diameter) and did not take into account the permeation of oxygen along the interface between the 104 bottleneck and cork coating. Therefore, it is particularly relevant to investigate the oxygen 105 transfer through the system composed of a cork stopper that has undergone a surface treatment 106 prior to being inserted in a glass bottleneck.

107

108 The present work examines the oxygen transfer at the interface between the glass bottleneck and 109 the cork stopper. In particular, we focus on the effect of surface treatment of the stopper on the 110 oxygen transfer at the glass-stopper interface. First, permeation experiments were performed for 111 uncompressed and compressed (40% in volume) micro-agglomerated stoppers to determine their 112 intrinsic oxygen diffusion coefficients and the effect of compression. Then, permeation 113 experiments were carried out on the system composed of the cork stopper without surface 114 treatment inserted in a glass bottleneck. In the final step, the oxygen transfer was evaluated on the 115 glass-stopper system with the stopper coated with a surface treatment product. This 116 comprehensive approach aimed to quantify and differentiate between the two oxygen flows 117 passing through the stopper and at the interface between the stopper and the glass.

118

119

5

120 2. MATERIALS AND METHODS

121

122 **2.1.** Cork stopper samples

Micro-agglomerated cork stoppers (of the type Diam 10) were produced by Diam Bouchage (Céret, France) by a molding process using cork particles associated with binding agents. The stoppers used for the experiments were 24.2 mm in diameter and 49 mm long and were either coated with an anionic emulsion of paraffin and silicone or were without a surface treatment agent. The different conditions used are summarized in figure 1.

128 2.1.1. <u>Compressed cork stopper</u>

Cork wafers 3 mm thick were cut in the middle of full-length cork stoppers. They were then inserted uncompressed in a metal ring and attached at the periphery with Araldite 2012 to avoid gas transfer at the interface. The experiments were carried out on 3 mm thick cork wafers to reduce the time of measurement.

133 2.1.2. <u>Compressed cork stopper</u>

Full-length cork stoppers were first compressed using a professional bottling machine comprising four stainless steel jaws (GAI 4040, France) and inserted in a metal ring of 18.5 mm diameter, corresponding to the diameter of the entry bore of a bottleneck (AFNOR, 2018). This operation leads to a 40% compression of the initial stopper volume. Similar to uncompressed cork stoppers, the interface between the cork wafer and the metal ring was glued to avoid gas transfer at the interface. Here, the cork samples were 6 mm thick to prevent buckling during compression.

140

2.1.3. Cork stopper inserted in a glass bottleneck

141 Uncoated full-length cork stoppers were inserted in empty glass bottles (Bourgogne Astre 37.5
142 cL, Verrerie de Bourgogne, France) using the same bottling machine. Prior to bottling, the

bottleneck profile of each bottle was measured using a profilometer (Egitron PerfiLab PRF 2014 01) to ensure they complied with the corresponding standard (AFNOR, 2018). The bottles were then cut below the stopper with a diamond cutoff wheel and inserted in a metal ring (Figure 2). Here, only the part between the ring and the bottleneck was glued with Araldite 2012. Oxygen transfer measurements were performed on 49-mm-long closures inserted in a bottleneck having an inner diameter of 18.5 ± 0.5 mm.

149 2.1.4. Cork stopper with surface coating

The same procedure was applied for cork stoppers coated with a surface treatment product. A coating composed of an emulsion of paraffin wax and silicone was sprayed in a drum coater at an industrial scale. For these stoppers, only 6 mm wafers were inserted in the bottleneck (Figure 2). This allowed the time of permeation experiment to be reduced. Ten measurements were performed for each of the four conditions chosen for this comprehensive study.

155

156 **2.2. Oxygen permeation**

During storage, we can distinguish between two phenomena; the oxygen given out by the stopper expressed by the oxygen initial release (OIR), and the oxygen coming from the outside environment expressed by the oxygen transmission rate (OTR) (Chevalier, Pons & Loisel, 2019). In this study, the OTR was determined using a homemade apparatus based on a manometric method (Figure 2).

The equipment and protocol have been detailed previously (Lagorce-Tachon et al., 2014; Lequin et al., 2012). The oxygen flow was measured through a sample separating two chambers. First, an oxygen purge was performed in the measuring chamber C_1 . The initial pressure was then set at around 900 hPa while the other compartment, C_2 , was kept under dynamic vacuum (0.1 hPa). 166 The decrease in oxygen pressure in the measuring compartment, caused by the transfer of oxygen 167 from compartment C_1 to, C_2 was monitored over time. The temperature was kept constant at 298 168 K (±1 K) by a water circulation surrounding compartment C_1 under thermostat control. The 169 pressure sensitivity was ± 0.1 hPa.

- 170
- 171 **2.3. Scanning electron microscopy**

Prior to bottling, agglomerated cork stoppers without and with surface treatment were observed by SEM using a Jeol JSM 7600F apparatus (3.5 kV). Before imaging, cork samples were cut with a razor blade, and coated with a carbon film (15–20 nm). The obtained images allowed us to visualize the distribution of the surface treatment product on the stopper surface as well as the thickness of the coating.

177 3. CALCULATION

178

179

3.1.Oxygen transfer in the cork stopper

180 Considering the gas as ideal, the surface molar flow of oxygen passing through the wafer, J_w 181 (mol.m⁻².s⁻¹) is given by the equation:

182

183
$$J_{W} = -\frac{1}{S_{W}}\frac{dn}{dt} = -\frac{V}{S_{W}.R.T}\frac{dp}{dt}$$
 (Equation 1)

184

185 *p* is the pressure (Pa) in the compartment C₁ along time *t* (s), *V* is the volume of the compartment 186 C₁ (m³), S_w is the surface of the wafer (m²), *R* is the ideal gas constant (8.314 J. mol⁻¹.K⁻¹) and *T* 187 is the temperature (K). 189 wafer, once the steady state is established, is also given by the equation: $J_w = -D_w \cdot \nabla C^a \approx -D_w \cdot \frac{C^a}{e}$ (Equation 2) 190 With D_w the diffusion coefficient (m².s⁻¹) of oxygen inside the wafer, e the thickness of the wafer 191 (m) and ∇C^a (mol.m⁻⁴) the concentration gradient of oxygen adsorbed on both side of the wafer. 192 C^{a} (mol.m⁻³) is related to the concentration of the gas C^{g} (mol.m⁻³) by the equation: 193 194 $C^a = \psi. C^g$ (Equation 3) 195 196 197 With ψ , so called the separation factor. Ψ is obtained from the sorption isotherm of oxygen, on 198 cork which has been determined on previous work(Lequin et al., 2012). 199 200 By combining the equations (1), (2) and (3), and after integration over time, we obtain: 201 $\ln\left(\frac{p_{t=0}}{p_t}\right) = \frac{D_W \cdot \psi \cdot S_W}{e \cdot V} \cdot t$ (Equation 4) 202 203 204 Thus, the diffusion coefficient of oxygen through the cork wafer is determined from the slope of the straight-line of the plot $\ln(\frac{p_{t=0}}{p_t}) = f(t)$ obtained once the steady state is established. 205 206 207

According to the first Fick's law, the surface molar flow of oxygen passing through the cork

188

3.2. Extrapolation of the diffusion coefficient for a full-length cork stopper

As cork stoppers are not homogeneous materials, the diffusion coefficient measured through a cork wafer of thickness *e* is not representative of the diffusion coefficient through a full-length cork stopper of length L_s . For the measurements made on wafers 3 or 6 mm thick, it was thus necessary to extrapolate the experimental results to a full-length cork stopper. To that end, the stopper was considered as a serial stack of *n* wafers, where each slice represents a local resistance to gas transfer, R_w . The sum of these resistances allowed us to calculate the total resistance R_s of the stopper, as defined by the following equations:

216
$$R_s = \frac{L_s}{D_s} = \sum_{i=1}^n R_{wi} = \sum_{i=1}^n \frac{e}{D_{wi}}$$
(Equation 5)

217
$$L_s = e.n$$
 (Equation 6)

218
$$\frac{1}{D_s} = \frac{1}{n} \sum_{i=1}^n \frac{1}{D_{wi}}$$
(Equation 7)

219 Where R_s is the overall resistance of the stopper, D_s is the extrapolated diffusion coefficient of the 220 stopper, L_s is the total length of the stopper, n is the total number of wafers contained in a full-221 length stopper and D_{wi} is the diffusion coefficient of the wafer i drawn at random in the statistical 222 distribution of diffusion coefficients determined experimentally.

223

3.3. Oxygen transfer at the glass-cork interface

The oxygen flow through the cork stopper-glass bottleneck interface, $J_{interface}$ (mol.m⁻².s⁻¹), is determined by subtracting from the total flow, J_{total} , going through the system comprising the cork stopper inserted in the glass bottleneck, the oxygen flow going through the cork stopper alone, J_s .

$$J_{interface} = J_{total} - J_s \qquad (Equation 8)$$

The total flow of gas passing through the bottleneck-cork system is expressed by an equationsimilar to Equation 1:

231
$$J_{total} = -\frac{1}{s}\frac{dn}{dt} = -\frac{V}{s.r.t}\frac{dp}{dt} \simeq -\frac{V}{s.r.t}\frac{\Delta p}{\Delta t}$$
(Equation 9)

As we know the diffusion coefficient of oxygen through the full-length cork stopper, D_s , the flow passing only through the cork stopper is calculated with the relation:

234
$$J_s = -D_s. S. \frac{\Delta p}{L_s.R.T}$$
 (Equation 10)

In the last two equations, *S* is the section area of the cork inserted in the bottleneck, and Δp is the pressure decrease in compartment C₁ during time, Δt .

- 237
- 4. RESULTS AND DISCUSSION
- 239

4.1. Role of the compression on the oxygen transfer

241 To determine the effect of compression on the gas transfer through the cork stopper, the effective 242 diffusion coefficient of oxygen was first measured on uncompressed and compressed cork 243 wafers, with the interface glued in both cases. The experimental and extrapolated oxygen 244 diffusion coefficient values for the compressed and uncompressed samples are given in Figure 3 245 and in Table 1. The effective oxygen diffusion coefficient through uncompressed 3 mm cork wafers was between 10⁻¹² m².s⁻¹ and 10⁻¹⁰ m².s⁻¹. For the compressed 6 mm cork wafers, the 246 247 effective diffusion coefficient values ranged from 10⁻¹¹ to 10⁻¹⁰ m².s⁻¹. These data were then 248 extrapolated to a full-length cork stopper (48 mm) for comparison using the model of series 249 resistances to mass transfer. From the statistical distribution, the oxygen diffusion coefficient value was reduced from 1.4 x 10^{-11} m².s⁻¹ for the uncompressed to 9.2 x 10^{-12} m².s⁻¹ for the compressed cork stoppers.

252 Thus, when compression corresponding to a reduction of 40% in volume is applied to the 253 stopper, this leads to a slight decrease in the oxygen transfer through the stopper with a reduction 254 of the oxygen diffusion coefficient by a factor of 1.5. With natural cork stoppers, Lagorce-255 Tachon et al. did not find a significant impact of compression on the diffusion coefficient of 256 oxygen after a 40% reduction in volume (with a diameter reduction from 24 mm to 18.5 257 mm)(Lagorce-Tachon et al., 2016). Indeed, the effective diffusion coefficients measured after compression led to a relatively large distribution of oxygen diffusion coefficients of 258 259 uncompressed cork ranging from 10^{-10} to 10^{-7} m².s⁻¹. In such a case, it is highly probable that the 260 heterogeneity between samples of natural cork (which are much more heterogeneous than 261 agglomerated cork) masked the effect of the compression. For agglomerated cork stoppers, the 262 statistical distribution of the effective diffusion coefficients for full-length stoppers were narrowed to values around 10⁻¹¹ m².s⁻¹, reflecting the homogeneity of the agglomerated cork 263 264 stoppers and indicating the effect of compression on oxygen transfer. These results also accord 265 with those reported by Rabiot *et al.* They measured oxygen permeability in dry condition for agglomerated cork wafers (10 mm thick) with the initial diameter of 24 mm compressed to final 266 267 diameters of 21 mm and 18.5 mm, which represent the lower and upper bottleneck diameters, respectively (Rabiot, Sanchez & Aracil, 1999). Such differences in the compression of the 268 269 stopper, corresponding to a reduction between 23% and 40% in volume, led to a decrease in oxygen permeability between 9.3 x 10⁻¹³ mol.m.m⁻².Pa⁻¹.s⁻¹ and 1.8 x 10⁻¹³ mol.m.m⁻².Pa⁻¹.s⁻¹, 270 271 respectively, which represents a reduction in oxygen permeability by a factor of 5. This decrease in the oxygen transfer through an agglomerated cork stopper could be attributed to a reduction in 272

the initial porosity between cork particles. This could vary according to the formulation of the agglomerated cork stopper, in particular with respect to the ratio of weight of adhesive to the weight of cork (Crouvisier-Urion et al., 2020).

276

4.2. Oxygen transfer at the stopper-bottleneck interface: role of the surface treatment

277 In the second step, the effective diffusion coefficient of oxygen through the whole stopper-278 bottleneck system was determined. First, this was calculated for stoppers with no surface 279 treatment and then for stoppers coated with an emulsion of paraffin and silicone. This allowed us 280 to evaluate the gas transfer at the stopper-bottleneck interface and to assess the impact of the 281 surface treatment on the oxygen diffusion. The experimental and extrapolated distributions of the logarithm of the diffusion coefficient of oxygen of the different samples are reported in Figure 4 282 283 and the mean oxygen diffusion coefficients extrapolated to a full cork stopper are displayed in 284 Table 1.

285 For the stopper without a surface treatment agent and inserted in the bottleneck, the mean 286 effective diffusion coefficient appeared significantly higher than that of cork stoppers alone (i.e., 287 outside the bottleneck) and with the same compression level. The mean value was $1.3 \times 10^{-7} \text{ m}^2 \text{ s}^{-1}$ ¹ for the former compared with 9.2 x 10^{-12} m².s⁻¹ for the latter. Such a stopper-bottleneck system 288 289 is thus much more permeable than a compressed stopper outside the bottleneck (with the 290 interface glued). The poor resistance to gas transfer of this system must therefore originate from 291 the stopper-glass interface, which thus addresses the likely role of defects (macropores, scratches, 292 roughness irregularities, etc.) formed on the cork surface during its processing or at the bottling 293 stage, or of defects present on the surface of the bottleneck. Such defects might constitute 294 preferential pathways for gas transfer.

The OTRs through the stopper-bottleneck systems and through the stoppers alone were also calculated to determine the OTR through the interface. These results are summarized in Table 1 and highlight that more than 99% of the total oxygen transfer occurs at the stopper-bottleneck interface. A similar result was previously found for natural cork with an effective diffusion coefficient 50 times higher for a natural whole cork stopper compressed in a bottleneck compared with a compressed stopper alone with the interface glued (Lagorce-Tachon et al., 2016). **Table 1.** Mean oxygen diffusion coefficients and OTRs determined for uncompressed and compressed

302 cork stoppers alone and for cork stoppers inserted in a bottleneck with and without a surface treatment 303 agent (extrapolated to a full cork stopper, from 10 replicates in each case; see figure 4 for corresponding 304 distributions). For practical reasons, OTR is expressed as mg.year⁻¹, referring to as mg of oxygen going 305 through the stopper per year.

	Effective Diffusion	OTR _{total}	OTR interface	OTR _{stopper} /OTR _{total}
	Coefficient D _s (x 10 ⁻¹² m ² .s ⁻¹)	(mg. year ⁻¹)	(mg. year ⁻¹)	(%)
Agglomerated uncompressed stopper (interface glued)	14.4 ± 2	0.61 ± 0.11	/	/
Agglomerated compressed stopper (interface glued)	9.2 ± 2	0.38 ± 0.08	/	/
Agglomerated stopper compressed in a bottleneck without surface treatment	130 000 ± 90 000	17 313 ± 4432	17 313	0.003
Agglomerated stopper compressed in a bottleneck with surface treatment	7.9 ± 2	0.34 ± 0.08	0	100

306

When the stopper is coated with a surface treatment agent, the effective oxygen diffusion coefficients through 6 mm cork wafers compressed in a bottleneck were around 8.8 x 10^{-12} m².s⁻¹. When extrapolated to a 48 mm cork stopper, the mean effective oxygen diffusion coefficient is 7.9 x 10^{-12} m².s⁻¹. This value is similar to that obtained previously for a compressed cork without any transfer at the interface (9.2 x 10^{-12} m².s⁻¹). Moreover, the OTR at the interface between the

stopper and the bottleneck is around 0.34 mg.year⁻¹ compared with 17 313 mg.year⁻¹ in the case 312 313 of a cork stopper compressed in a bottleneck without surface treatment. When coated with a 314 surface treatment product, the oxygen flow at the interface decreases significantly and the 315 effective diffusion coefficient becomes 10 000 times lower. These results emphasize the crucial 316 role played by the surface treatment agent present between the stopper and the glass bottleneck 317 on oxygen transfer. This thin layer coating appears to provide an efficient barrier against the 318 ingress of oxygen from the external environment into the bottle. In addition to its primary 319 function of facilitating uncorking, it can act as well as lubricating agent at bottling (during the 320 compression and insertion stages) by reducing the creation of defects on the outer stopper 321 surface. It can also act as an additional barrier to oxygen transfer by masking defects at the 322 interface between the stopper and the bottleneck, providing an oxygen permeability as low as the 323 cork stopper itself.

324

325 It should be noted that all analyses of oxygen transfer were performed under conditions that differ 326 from oenological conditions (i.e., a dry sample under vacuum and without partial pressure of 327 water and ethanol vapors). In a bottleneck, the cork is in contact with the wine (if bottles are 328 stored horizontally) or in contact with a vapor phase saturated with water and ethanol vapors (if 329 the bottles are stored vertically). These conditions might also affect the barrier properties of 330 stopper. Further experiments are clearly needed to fully understand how the global diffusion 331 coefficient of oxygen through cork could change depending on hydration or the presence of 332 ethanol.

333

4.3. Microscopic characterization of the surface coating

335 In addition to permeability measurements, SEM analysis was performed for agglomerated 336 stoppers with and without coating. The corresponding microscopic images of the cork stopper 337 surface are presented in Figure 5. First, the stopper surface without coating is shown in Figure 338 5A-B. The cork particles, as well as microspheres, are entrapped within the adhesive network that 339 maintains the cohesion of the stopper. As the cork particles have no specific orientation, this 340 confers more isotropy at the macroscopic scale, to the agglomerated stopper compared to the natural cork stopper having a strong anisotropy due to the specific orientation of cork cells 341 342 (Gibson, Easterling & Ashby, 1981).

343 Surface treatment of the stopper, performed by drum coating with paraffin wax and silicone 344 emulsion, results in a thin coating layer that can be observed on the stopper surface (Figures 5C-345 D). The deposited coating layer fully covers the surface of the stopper and does not tend to form 346 aggregates (Fig 5C). It is also distributed in a very thin layer over the cork cells and does not fill 347 the volume of the outer empty cells. Such SEM observation was performed at the scale of a 1 mm² surface and is representative of the whole coated stopper surface. However, only small-scale 348 349 observations could be performed with SEM microscopy. This method unfortunately does not 350 enable a full assessment of the homogeneity of the coating on the surface of the whole stopper. 351 Nevertheless, even if qualitative, these results seem to indicate that the coating was 352 homogeneously distributed on the stopper surface, at the scale of observation provided by SEM.

At a lower scale, the coating thickness could be estimated from cross-sectional images at around 0.5 μ m (Fig 5d) and was quite thin in view of the coating process. This thickness was much lower than the 17 μ m (paraffin wax layer) reported by Keenan *et al.* on natural cork stoppers (Keenan, Gozukara, Christie & Heyes, 1999). However, this last value was calculated from the weight and density of the paraffin. The weight value was obtained by solvent extraction of the wax layer

358	from cork stoppers. This result could thus be overestimated because of the solvent extraction of		
359 other compounds from the cork in addition to those used for the surface treatment.			
360			
361			
362			
363			
364			
365			
366	5. CONCLUSIONS		
367			

The transfer of oxygen in a cork/bottleneck system was assessed through a comprehensive study 368 369 starting from the effective diffusion through the stopper alone and ending with a more complex 370 system comprising the stopper covered by a surface treatment agent and compressed in the glass 371 bottleneck. First, the effect of compression on agglomerated cork (with the interface glued) 372 showed that a 40% reduction in the volume of the stopper (compression applied for still wines) 373 reduced the effective oxygen diffusion of the stopper by 35%. Then, the oxygen transfer through 374 a corked bottleneck was examined. Without coating, the oxygen effective diffusion coefficient 375 through an agglomerated cork stopper compressed in a bottleneck was significantly higher than through the stopper alone (10⁻⁷ m².s⁻¹ vs 10⁻¹¹ m².s⁻¹). However, when the stopper was coated 376 with a silicone-paraffin emulsion, the effective oxygen diffusion coefficient through the cork-377 bottleneck gave a similar value to that of the compressed stopper (10⁻¹¹ m².s⁻¹). These results 378 379 clearly highlighted the crucial role of the surface treatment in oxygen transfer through a corked 380 bottleneck. A coating with a thickness of less than 0.5 µm provided an efficient barrier for the 381 stopper-bottleneck interface system to act against gas transfer at the interface. In addition to its initial role of ensuring easier uncorking, the surface coating therefore confers an additional andunexpected barrier efficiency to the wine sealing system.

384

385 AUTHOR CONTRIBUTIONS

- 386 T.K., J.C. and J.-P.B. designed research; T.K., R.D.G., J.C. and J.-P.B. performed research;
- T.K., J.C., R.D.G. and J.-P.B. analyzed data; and T.K., J.C., R.D.G., and J.-P.B. wrote the paper.
- 389

390 ACKNOWLEDGMENTS

We gratefully acknowledge Diam Bouchage as well as the French National Association of Research and Technology (ANRT) for their financial support and the PhD grant (CIFRE 218-1278) of Julie Chanut. SEM images were determined at the Laboratoire Interdisciplinaire Carnot de Bourgogne with the help of Frédéric Herbst. We acknowledge the Bureau Interprofessionnel des Vins de Bourgogne for providing bottling machine and profilometer as well as Verrerie de Bourgogne for donating the bottles.

397

398 COMPETING INTERESTS STATEMENT

- 399 The authors declare no competing interests.
- 400
- 401
- 402

403 REFERENCES

404

405 AFNOR. (2018). NF EN 12726 Emballage - Bague plate unique ayant un diamètre d'entrée de 18,5 mm
 406 pour bouchage liège et capsule témoin d'effraction. La Plaine Saint-Denis

- 408 Arapitsas, P., Speri, G., Angeli, A., Perenzoni, D. & Mattivi, F. (2014). The influence of storage on the 409 "chemical age" of red wines. *Metabolomics*, *10*, 816-832. https://doi.org/10.1007/s11306-014-0638-x
- 410

407

- 411 Caloghiris, M., Waters, E. J. & Williams, P. J. (1997). An industry trial provides further evidence for the 412 role of corks in oxidative spoilage of bottled wines. *Australian Journal of Grape and Wine Research, 3,* 9-
- 413 17. https://doi.org/10.1111/j.1755-0238.1997.tb00110.x
- 414
- Chatonnet, P. & Labadie, D. (2003). Contrôle de la conformité des bouchons: objectifs et paramètres à
 l'usage des professionnels. *Revue française d'oenologie, 198,* 20-29.
- 417
 418 Chevalier, V., Pons, A. & Loisel, C. (2019). Impact de l'obturateur sur le vieillissement des vins en
 419 bouteille Partie 1/3 Caractérisation des transferts d'oxygène de bouchons en liège. *Revue des*420 *Oenologues, 170,* 40-43.
- 421

425

422 Crouvisier-Urion, K., Bellat, J.-P., Gougeon, R. D. & Karbowiak, T. (2018). Gas transfer through wine 423 closures : A critical review. *Trends in Food Science & Technology, 78,* 255-269. 424 https://doi.org/10.1016/j.tifs.2018.05.021

- 426 Crouvisier-Urion, K., Bellat, J.-P., Liger-Belair, G., Gougeon, R. & Karbowiak, T. (2020). Unravelling CO2 427 transfer through cork stoppers for Champagne and sparkling wines. *Food Packaging and Shelf Life, In* 428 *Press.*
- 430 Fortes, M. A., Rosa, M. E. & Pereira, H. (2004). *A Cortiça*. I. Press, Lisboa
- 431

434

429

432 Gibson, L. J., Easterling, K. E. & Ashby, M. F. (1981). The structure and mechanics of cork *Proceedings of* 433 *the Royal Society of London, 377,* 99-117. https://doi.org/10.1098/rspa.1981.0117

- Gonzalez-Adrados, J. R., Garcia-Vallejo, M. C., Caceres-Esteban, M. J., Garcia de Ceca, J. L., GonzalezHernandez, F. & Calvo-Haro, R. (2011). Control by ATR-FTIR of surface treatment of cork stoppers and its
 effect on their mechanical performance. *Wood Science and Technology, 46,* 349-360.
 https://doi.org/10.1007/s00226-011-0403-5
- Gonzalez-Adrados, J. R., Gonzalez-Hernandez, F., Garcia de Ceca, J. L., Caceres-Esteban, M. J. & GarciaVallejo, M. C. (2008). Cork-Wine Interaction studies : Liquid absorption and non-volatile compound
 migration *J. Int. Sci. Vigne Vin, 42,* 161-166. https://doi.org/10.20870/oeno-one.2008.42.3.815
- 443

439

Karbowiak, T., Crouvisier-Urion, K., Lagorce, A., Ballester, J., Geoffroy, A., Roullier-Gall, C., Chanut, J.,
Gougeon, R. D., Schmitt-Kopplin, P. & Bellat, J.-P. (2019). Wine aging: a bottleneck story. *Npj Science of Food, 14*, https://doi.org/10.1038/s41538-019-0045-9

447

Karbowiak, T., Gougeon, R. D., Alinc, J.-B., Brachais, L., Debeaufort, F., Voilley, A. & Chassagne, D. (2010).
Wine oxidation and the role of cork. *Critical Reviews in Food Science and Nutrition, 50,* 20-52.
https://doi.org/10.1080/10408398.2010.526854

Keenan, C. P., Gozukara, M. Y., Christie, G. B. Y. & Heyes, D. N. (1999). Oxygen permeability of macrocrystalline paraffin wax and relevance to wax coatings on natural corks used as wine bottle closures. *Australian Journal of Grape and Wine Research, 5,* 66-70. https://doi.org/10.1111/j.1755-0238.1999.tb00154.x

455

Lagorce-Tachon, A., Karbowiak, T., Paulin, C., Simon, J.-M., Gougeon, R. D. & Bellat, J.-P. (2016). About the role of the bottleneck/cork interface on oxygen transfer. *Journal of Agricultural and Food Chemistry*, *64*, 6672-6675. https://doi.org/10.1021/acs.jafc.6b02465

459

463

466

Lagorce-Tachon, A., Karbowiak, T., Simon, J.-M., Gougeon, R. D. & Bellat, J.-P. (2014). Diffusion of oxygen through cork stopper: Is it a Knudsen or a Fickian mechanism? *Journal of Agricultural and Food Chemistry, 62*, 9180-9185. https://doi.org/10.1021/jf501918n

Lefebvre, A., Riboulet, J.-M., Alegoet, C., Pouillaude, C., Lacorne, F. & Natividade, J. V. (2006). Charte des bouchonniers liègeurs. Paris, France

Lequin, S., Chassagne, D., Karbowiak, T., Simon, J.-M., Paulin, C. & Bellat, J.-P. (2012). Diffusion of oxygen
in cork. *Journal of Agricultural and Food Chemistry, 60,* 3348-3356. https://doi.org/10.1021/jf204655c

Lopes, P., Saucier, C., Teissedre, P.-L. & Glories, Y. (2006). Impact of storage position on oxygen ingress
through different closures into wine bottles. *Journal of Agricultural and Food Chemistry, 54,* 6741-6746.
https://doi.org/10.1021/jf0614239

473

Lopes, P., Saucier, C., Teissedre, P.-L. & Glories, Y. (2007a). Main Routes of oxygen ingress through different closures into wine bottles. *Journal of Agricultural and Food Chemisty*, *55*, 5167-5170. https://doi.org/10.1021/jf0706023

477

478 Lopes, P., Saucier, C., Teissedre, P.-L. & Glories, Y. (2007b). Oxygen transmission through different
479 closures into wine bottles. *Practical Winery & Vineyard*480

Lopes, P., Silva, M. A., Pons, A., Tominaga, T., Lavigne, V., Saucier, C., Darriet, P., Cabral, M., Teissedre, P.L. & Dubourdieu, D. (2012). Impact of the Oxygen Exposure during Bottling and Oxygen Barrier
Properties of Different Closures on Wine Quality during Post-Bottling. in: *Flavor Chemistry of Wine and*Other Alcoholic Beverages (pp. 167-187)

Rabiot, D., Sanchez, J. & Aracil, J. M. (1999). Study of the oxygen transfer through synthetic corks for
wine conservation. *Second Europeen congress of chemical engineering*, Montpellier, France

Roullier-Gall, C., Hemmler, D., Gonsior, M., Li, Y., Nikolantonaki, M., Aron, A., Coelho, C., Gougeon, R. D.
& Schmitt-Kopplin, P. (2017). Sulfites and the wine metabolome. *Food Chemistry, 237,* 106-113.
https://doi.org/10.1016/j.foodchem.2017.05.039

492

485

493 Roullier-Gall, C., Witting, M., Moritz, F., Schmitt-Kopplin, P. & Gougeon, R. (2016). Natural oxygenation 494 of Champagne wine during the prise de mousse: a metabolomics picture of hormesis. *Food Chemistry*,

495 *203,* 207–215. https://doi.org/10.1016/j.foodchem.2016.02.043

496

500

497 Venturi, F., Sanmartin, C., Taglieri, I., Xiaoguo, Y., Andrich, G. & Zinnai, A. (2016). The influence of 498 packaging on the sensorial evolution of white wine as a function of the operating conditions adopted 499 during storage. *Agrochimica*, *60*, 150-159. https://doi.org/10.12871/0021857201627

501 Waters, E. J. (1997). Random post-bottling oxidation of bottled wines. *Australian Grapepower and* 502 *Winemaker, 408,* 46-47.

503

504 Waters, E. J., Peng, Z., Pocock, K. F. & Williams, P. J. (1996). The role of corks in oxidative spoilage of 505 white wines. *Australian Journal of Grape and Wine Research*, 191-197. https://doi.org/10.1111/j.1755-506 0238.1996.tb00108.x

507

508 Waters, E. J., Skouroumounis, G., Sefton, M. A., Francis, I. L., Peng, Z. K. & Kwiatkowski, M. (2001). The 509 inherent permeability of corks to oxygen *Australian Wine Institut 46th Annual Report, 31*

510

Figure 1. Conditions used for the measurement of oxygen transfer.

Figure 2. Scheme of the homemade manometric device for the oxygen transfer measurement of the different cork samples

Figure 3. Experimental and extrapolated distributions of the logarithm of the diffusion coefficient of oxygen of uncompressed and compressed agglomerated cork stoppers at 298 K obtained from 10 replicates. Green dashed line (--): experimental distribution of a 3 mm uncompressed cork wafer. Blue dashed line (--): experimental distribution of a 6 mm compressed cork wafer (from 10 replicates). Green line (-): extrapolated distribution to a 48 mm stopper from the experimental data measured for 3 mm uncompressed cork wafers. Blue line (-): extrapolated distribution to a 48 mm stopper from the experimental data measured for 3 mm uncompressed cork wafers. Blue line (-): extrapolated distribution to a 48 mm stopper from the experimental data measured for 6 mm compressed cork wafers.

Figure 4. Distributions of the logarithm of the diffusion coefficient of oxygen at 298 K obtained from 10 replicates. Green (-): extrapolated distribution to a 48 mm stopper from the experimental data for 3 mm compressed cork wafers. Blue (-): extrapolated distribution to a 48 mm stopper from the experimental data for 6 mm compressed cork wafers. Red (-): experimental distribution of 48 mm stoppers compressed in a bottleneck without surface treatment. Yellow (-): extrapolated distribution to 48 mm stoppers from the experimental data measured for 6 mm cork wafers compressed in a bottleneck with surface treatment (emulsion of paraffin and silicone).

Figure 5. SEM observations of the surface of agglomerated stoppers observed at different magnifications factors. a) without surface treatment, b) cross section of agglomerated cork stopper without surface treatment c) with surface treatment, d) cross section of an agglomerated cork stopper with surface treatment.

Table 1. Mean oxygen diffusion coefficients and OTRs determined for uncompressed and compressed cork stoppers alone and for cork stoppers inserted in a bottleneck with and without a surface treatment agent (extrapolated to a full cork stopper, from 10 replicates in each case; see figure 4 for corresponding distributions). For practical reasons, OTR is expressed as mg.year⁻¹, referring to as mg of oxygen going through the stopper per year.



Figure 2



Figure 3



Figure 4





Coating Cork cell wall

Graphical abstract

